

HS 80 - QUICK SET HIGH EARLY STRENGTH GROUT

Auscon HS 80 Technical Data Sheet

Auscon HS 80 Quick Setting High Early Strength Cement Grout is a Class-C one-component cement powder which requires only the addition of water to form a high early quick setting non-shrink grout. Suitable for civil engineering applications, where a quick and high early strength is required. It incorporates specially graded aggregates and advanced new generation polymers to form a cementitious grout. HS 80 has high impermeability; this gives the material better resistance to water infiltration. Firms in approximately 20 minutes.

Advantages and Solution

- High Early Strength
- Pre-mix - just add water
- Quick Setting Firms in 20 minutes
- Balustrading Installation,
- Filling Voids & Gaps in Concrete
- Concrete, Stone, Masonry embedment

Mixing Instructions

1. Place 80% of the water into the mixing vessel.
2. Slowly add 70% of the powder to the mixing vessel and mix for 1 minute.
3. Add the final 20 % of the water to the mixing vessel.
4. Slowly add the remainder of the powder to the mixing vessel.
5. Mix for 3 minutes or until uniform to a homogenised workable mix

Water Ratio Limits	Litres per 20 kg bag
Flowable	4.2 – 4.3

Applying Mixed Material

- Application thickness: 10 mm to 100 mm.
- Do not exceed the recommended thickness in any layer.
- Do not mix more material than can be placed in 15 minutes.
- Protected HS 80 during curing time from rain and water
- Apply small amounts of mixed material into the surface and trowel to a smooth finish.

IMPORTANT: Do not mix cementitious products if the temperature is expected to exceed 30 °Celsius, or if the change in ambient temperature exceeds +/- 12 °Celsius

Surface Preparation

- All defective host substrate must be removed prior to application.
- Defective material includes cracked or structurally weakened surfaces.
- Host concrete must be roughened and aggregate exposed to ensure a good bond.
- Priming the surface with Auscon Bond 007 Primer is recommended.
- For chloride contaminated concrete, a concrete corrosion expert must be consulted.

All surfaces must be free from dust, oils, and surface contaminants. This may require cleaning with high-pressure water blasting or saturation to the surface using water before applying materials



For More Information contact Auscon Australia

HS 80 - QUICK SET HIGH EARLY STRENGTH GROUT

Auscon HS 80 Technical Data Sheet

Test Characteristic

Property	Test Method	Results
Cement	AS 3972	Complies
Chloride Content	AS 3972 Requirement - Max 0.10 %	0.01 %
Sulphur SO ₃	AS 3972 Requirement - Max 3.5%	2.4%
Volume Change	AS1478.2	<1.8%
Initial Set (Approximate)	AS 1012.18	15-25 minutes @ 20 °C
Final Set (Approximate)	AS 1012.18	70 minutes @ 20 °C
Flow Characteristics	AS 1478.2 (Appendix C)	< 51 Seconds
Compressive Strength	AS 1478.2 (Appendix A)	Complies
Maximum Particle Size	0.6 mm	
Mixing Time	3 - 4 Minutes	
Yield per (Approximate)	12 litres per 20kg	
Pump Life (Approximate)	15 minutes @ 20°C	

Compressive Strength

Minimum MPa	@ 1 Hour	@ 3 Hours	@ 24 Hours	@ 7 Days	28 Days	Water / 20kg
Flowable	20	25	30	55	65	4.2

The Data testing was conducted in a controlled laboratory environment field results may vary and is beyond Auscon Australia control

- **Storage** - Store undercover in cool, dry conditions.
- **Shelf Life** - 12 Months if unopened and kept in a dry location. Best to use within 6 months from purchase date.
- **Clean up** - Clean tools and surfaces using clean water within 30 minutes of applying materials or prior to curing.
- **Packaging** – 1 tonne bulk bags and 20kg paper bag, 48 bags per pallet, pallet weight 990kg, (including pallet).
- **Disposal** - Keep out of sewer and stormwater lines. In the interest of the environment, please dispose of empty bag and materials as trade waste in accordance with local authority guidelines.
- **Safety Information** - The end-user of this product must first read the latest version of the Safety Data Sheets at www.auscon.net.au before this product can be used.

Auscon products are manufactured using ISO 9001 Certified Processes.

Version – June 2020

DISCLAIMER - The end use of this product is beyond the manufacturer's control and liability is restricted to the replacement of material proven to be faulty. The manufacturer is NOT responsible for any loss or damage arising from incorrect usage of this product. The information contained herein is provided in good faith and to best of Auscon Australia knowledge is true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of the product for an application.

Users are requested to check that the literature in their possession is of the latest and correct issue, Auscon is a registered trademark of Auscon Australia Pty Ltd.

The recommendations to the application and use of the Auscon Australia cement products are based on materials mixed and applied under normal conditions. Site conditions and substrates will vary.

The product must be first tested to its suitability of the intended application before use. The end-user of this product must first read the latest version of the Technical & Safety Data Sheets at www.auscon.net.au before this product can be used.



For More Information contact Auscon Australia

Ph 1300 988 964