

# BITUTHENE<sup>®</sup> Primer Type C

VOC-free primer and curing compound

---

## Product Description

A liquid membrane curing compound and primer for BITUTHENE<sup>®</sup> membranes. It consists of water dispersed non-volatile solids. After application, the water evaporates leaving a thin impermeable film over the surface.

## Product Uses

BITUTHENE<sup>®</sup> Primer Type C is designed for concrete, brick and masonry substrates to which any BITUTHENE<sup>®</sup> selfadhesive sheet membrane will be applied. It is also a Class 3 Type Z curing blanket for freshly placed concrete.

## Features

- Complies with Green Star requirements
- It facilitates moisture retention in the concrete giving maximum strength and durability.
- Based on a fine particle bitumen emulsion to give a tenacious, vapour proof bond to the substrate.
- Certified curing compound to AS3799:1998.
- Non-hazardous – no VOC
- Quick drying and low odour

## Preparation

Surfaces must be sound clean, free from dust, oil, grease or contaminants. Do not apply when rain is expected.

## Application

Mix thoroughly immediately prior to use and agitate product during application.

Apply one full coat forming a continuous film at a rate of 5m<sup>2</sup> / L by brush, broom, roller or low pressure spray. Allow to dry and apply the BITUTHENE<sup>®</sup> waterproof membrane in accordance with manufacturer's instructions.

## Typical Properties

Colour	Black
S.G.	0.95 – 1.0g / ml
Viscosity	>0.050Pa.s
Water Retention (AS3799.3.1.2)	90%
Drying Time @ 25 °C	1½ – 2 hours

VOC

0%

If using as curing compound, apply a further coat after a minimum 7 days cure. Early application of membrane may increase moisture vapour bubbles under BITUTHENE®.

## Compatibility

BITUTHENE® Primer Type C is designed for use under all Bituthene waterproof membrane systems.

## Coverage

BITUTHENE® Primer Type C is ready to use straight from container. Application rate is 5 to 6m<sup>2</sup> / L using brush roller or spray application. Coverage may vary depending on ambient temperature, porosity and texture of surface.

## Packaging

Packed in 20 litre pails or 200 litre drums.

## Storage

Store pails in a cool dry place. Unopened containers have a shelf life of 12 months from the date of manufacture.

## Clean Up

Remove uncured product with water. GP Solvent or Kerosene will assist with the removal of cured product. Exercise care when using solvents. Please review all Materials Safety Data Sheet before use.

## Technical Services

For assistance with working drawings for projects and additional technical advice, please contact GCP Applied Technologies.

Release Date: 02/11/18. The information contained in this product data sheet supersedes all previous versions.

[gcpat.com.au](http://gcpat.com.au) | For technical information: [anz.enq@gcpat.com](mailto:anz.enq@gcpat.com)

Australia 1800 334 444 New Zealand 0800 552 235 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898 India +91 124 402 8972 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133 Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

BITUTHENE is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2019 GCP Applied Technologies, Inc. All rights reserved.

Printed in Australia GCP PDS 054 07/17

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com.au](http://www.gcpat.com.au). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-07-06

[gcpat.com.au/solutions/products/bituthene-post-applied-waterproofing/bituthene-primer-type-c](http://gcpat.com.au/solutions/products/bituthene-post-applied-waterproofing/bituthene-primer-type-c)