

Multibond SMX25

Revision: 13/10/2021

Page 1 from 2

Technical data

Basis	SMX Hybrid Polymer
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 30 min
Curing speed * (23°C/50% R.H.)	3 mm/24h
Hardness**	25 ± 5 Shore A
Density	1,55 g/ml
Maximum allowed distortion (ISO 11600)	± 25 %
Max. tension (ISO 37)**	0,95 N/mm ²
Elasticity modulus 100% (ISO 37)**	0,50 N/mm ²
Elongation at break (ISO 37)**	> 500 %
Temperature resistance**	-40 °C → 90 °C
Application temperature	5 °C → 35 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Multibond SMX25 is a high quality, neutral, elastic, 1-component joint sealant based on SMX-Polymer.

Properties

- Good adhesion on most common building materials.
- Easy to tool, extrude (even at low temperatures) and finish in all weather conditions.
- Phthalate-free
- Stays elastic after curing.
- No odour
- No bubble formation within sealant in high temperature and humidity applications.
- Primerless application on many substrates (except where water pressure may occur)
- Can be painted with water based systems
- Good weather and UV resistance
- Solvent, halogen, acid and isocyanate free.

Applications

- Expansion and connection joints in the building industry: sealing of joints in prefabricated buildings, sealing between window and door frames,...

- Applications where the sealant needs to be overpainted with water based paints and varnishes.

Packaging

Colour: concrete grey, beige, dark grey, white, old white, black, sandstone, anemone, other colors on request

Packaging: 600 ml foil bag, other packaging on request

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Chemical resistance

Good resistance to (salt)water, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, diluted mineral acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Substrates

Substrates: all usual building substrates, aluminium, stone, treated wood, PVC, ...
Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Porous surfaces should

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Multibond SMX25

Revision: 13/10/2021

Page 2 from 2

be primed with Primer 150. Prepare non-porous surfaces with a Soudal activator or cleaner (see Technical Data Sheet). Not suitable for PE, PP, PTFE (eg Teflon®), bituminous substrates, copper or copper-containing materials such as bronze and brass. We recommend a preliminary adhesion and compatibility test on every surface.

Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

Application method

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Remarks

- Multibond SMX25 may be overpainted with water based paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.
- The drying time of alkyd resin based paints may increase.
- Multibond SMX25 can not be used as a glazing sealant.
- Multibond SMX25 is non staining and suitable for sealing on natural stone on condition the joint dimensions and joint movement are respected. Avoid permanent pressure on the sealant.

- When applying, make sure not to spill any sealant on the surface of materials. Taping the surface around the joint can prevent this.
- A total absence of UV can cause a color change of the sealant.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Not suitable for bonding aquariums.
- Do not use in applications where continuous water immersion is possible.
- Multibond SMX25 has a good UV resistance but can discolour under extreme conditions or after very long UV exposure.
- Discoloration due to chemicals, high temperatures, UV-radiation may occur. A change in color does not affect the technical properties of the product.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.

Standards and certificates

- U.S.: ASTM C920 type S, grade NS class 25

Environmental clauses

Leed regulation:

Multibond SMX25 conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.