



## Technical Data Sheet

# Simson ISR 70-05 AP

### Description

SIMSON ISR 70-05 AP is a Silyl Modified Polymer (SMP) based adhesive with a high tensile strength and is suitable for making elastic constructive joints. SIMSON ISR 70-05 AP can also be used as a sealant. SIMSON ISR 70-05 AP has been tested and certified to the International Maritime Organisation Fire Test Procedures for Surface Flammability, resolution A.687 and is approved for bonding deck materials onto steel or aluminium.

### Features

Solvent, isocyanate and PVC free.  
Very good UV-resistance and ageing properties.  
In general good adhesion on several substrates without the use of a primer.  
Permanent elastic within temperatures from  $-40^{\circ}\text{C}$  till  $+120^{\circ}\text{C}$ .  
Neutral, odourless and fast curing.  
Paint compatible with most industrial paint- or lacquer systems, both alkyd resin and dispersion based (due to the large scale of different types of industrial paints a paint compatibility test is recommended).  
Paintable after skin forming (wet on wet); this will not influence the curing speed.

### Recommended Uses

Elastic bonding and sealing in e.g. bus, caravan, train and yacht construction.  
Bonding of roofs on busses, trains, trucks.  
Bonding of corner profiles of aluminium or polyester on trailers.  
Bonding of polyester parts on metal frames.  
Bonding of floor systems.

### Application Instructions

#### Surface Preparation

In general SIMSON ISR 70-05 AP adheres well without primer on clean, dry, dust and grease free substrates of aluminium, stainless steel, galvanised steel, zinc, copper, brass, powder coated metal, most lacquered metal surfaces, glass, PVC, polyester (GRP), painted and lacquered wood, etc. No adhesion on untreated polyethylene, polypropylene and teflon. In those cases where due to great thermal or physical loads, especially under wet conditions, high adhesion demands are needed, the use of Simson Prep M is recommended. Prep M degreases and prepares the surface of the substrate in one step. On plain, untreated wooden surfaces and other porous substrates Simson Prep P is recommended. For more details concerning Prep M and Prep P, consult the specific technical data sheets. For other substrates and additional information consult Bostik.

#### Application of Simson ISR 70-05 AP

SIMSON ISR 70-05 AP can easily be extruded with a hand or air pressure gun at temperatures between  $+5^{\circ}\text{C}$  and  $+35^{\circ}\text{C}$ . In sealing applications SIMSON ISR 70-05 AP should be tooled or smoothed within 10 minutes (at  $20^{\circ}\text{C}/50\% \text{ R.H.}$ ) with a spatula or putty knife, occasionally moistened with a soap solution.

Avoid soap solution penetrating between joint sides and sealant, because this will cause loss of adhesion.

In bonding applications, the substrates must be assembled within 15 minutes (at  $20^{\circ}\text{C}/50\% \text{ R.H.}$ ) after applying SIMSON ISR 70-05 AP.

In general, an adhesive thickness of 2 mm is recommended.

At a temperature of  $20^{\circ}\text{C}$  and a relative humidity of 50%, SIMSON ISR 70-05 AP can be painted with the most industrial paints 10 minutes after application. Best adhesion of paint coats is generally obtained if painted within 4 hours after applying SIMSON ISR 70-05 AP.





## Technical Data Sheet

# Simson ISR 70-05 AP

### Clean up after Installation

Excess material should be removed by wiping with clean dry cloth. Remaining material should be cleaned with Bostik Handi-Clean Towels or IPA (Iso propyl alcohol).

### Properties

<b>Colour/s:</b>	Black, Grey and White
<b>Basic Material:</b>	Silyl Modified Polymer (SMP)
<b>Specific gravity:</b>	Approx. 1.5
<b>Curing Method:</b>	Moisture
<b>Skin Forming Time:</b>	approx. 15 minutes (20°C/50% R.H.)
<b>Open Time</b>	Up to 15 min (20°C/50% R.H.)
<b>Tensile Stress at Break</b>	approx. 2.9 Mpa (DIN 53504/ISO37)
<b>Elongation at Break</b>	approx. 250% (DIN 53504/ISO37)
<b>Shear Stress</b>	approx. 2.4 Mpa (DIN 53283/ ASTM D1002)
<b>Isocyanate Percentage</b>	0%

<b>Curing Speed after 24hrs</b>	approx. 3 mm (20°C/50% R.H.)
<b>Shore A Hardness</b>	approx. 60 (DIN 53505)
<b>Volume Change</b>	<3% (DIN 52451)
<b>Tear Propagation</b>	approx. 16N/mm (DIN 5315/ISO34)
<b>Tensile Stress (100%)</b>	Approx. 2.3 Mpa (DIN 53504/ISO37)
<b>Temperature Resistance</b>	-40°C to +120°C
<b>Solvent Percentage</b>	0%
<b>Application Temperature</b>	+5°C to +35°C
<b>UV-and Weather Resistance</b>	Very Good
<b>Chemical Resistance</b>	Good

### Storage & Shelf Life

Store in a cool, dry place, out of direct sunlight. Storage areas must be well ventilated and comply with Local, State and Federal regulations. For maximum shelf life, store between 5° and 20°C.

Shelf life is up to 12 months in sausages and up to 18 months in cartridges when stored in original, unopened containers, under the above conditions.

### Health & Safety

Obtain and read Material Safety Data Sheet, for details on Health and Safety information, prior to use of the material.

### Packaging

Simson ISR 70-05 AP is available in 290 ml cartridges and 600 ml sausages.

### Product Details

Item Number	Size	Colour	Pack Quantity
273563	290ml Cartridge	Black	12
371718	600ml Sausage	Black	12
279242	290ml Cartridge	Grey	12
379611	600ml Sausage	Grey	12
273546	290ml Cartridge	White	12
379638	600ml Sausage	White	12



## Technical Data Sheet

# Simson ISR 70-05 AP

The representations and recommendations regarding the products are based on tests which we believe to be reliable. However, no guarantee of their accuracy can be made because of the great range of field conditions and variations encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with a limited warranty only, and on the condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik Australia Pty Ltd be liable to anyone except for replacement of the products or refund of the purchase price.

### **ALL SALES ARE EXPRESSLY LIMITED TO THE TERMS AND CONDITIONS OF SALE OF BOSTIK AUSTRALIA PTY LTD**

Head Office      Bostik Australia Pty Ltd, 51-71 High Street, Thomastown Vic 3074  
A.B.N. 79 003 893 838  
Phone: (03) 9279 9333      Fax: (03) 9261 4744  
Phone Industrial:      Toll free 1300 560 799

Branches:      Sydney:      21 Tattersall Road, Kings Park NSW 2148  
Brisbane:      Building 6, 2404 Logan Road, Eight Mile Plains Qld 4113  
Perth:      12 Thorpe Close, Welshpool WA 6016

Product:      Simson ISR7005 AP  
Issue Date:      01/08/2014  
Issue No.:      1  
Author:      David V Stuart  
Division:      Industrial Adhesives  
Total Pages:      3



Quality  
ISO 9001

SAI GLOBAL

Quality endorsed ISO9001 (Thomastown site)  
TS16949 (Automotive).