

Megapoxy 55

LOW VISCOSITY CASTING EPOXY

Description

MEGAPOXY 55 is a specially formulated unfilled epoxy encapsulating and casting system. It offers high impact resistance with excellent electrical properties.

Typical Uses

- ⊕ Encapsulation of electrical power transformers
- ⊕ Electrical power cable jointing and terminating
- ⊕ Mould construction

Features

- ⊕ High impact resistance
- ⊕ Long pot life, low exotherm
- ⊕ High mechanical strengths
- ⊕ Excellent chemical resistance
- ⊕ Excellent electrical properties

Packaging

30 kg kit. Part A- 15litres, Part B- 10 litres.

Technical Data

Product as supplied

- ⊕ Part A epoxy resin - clear liquid
- ⊕ Part B formulated hardener - amber liquid

Mix Ratio

3 parts A to 2 parts B by Volume

Cured Properties

- ⊕ Density approx.: 1.1 kg per litre
- ⊕ Maximum Operating Temperature: 90°C
- ⊕ Martens Heat Distortion Temperature: 60°C
- ⊕ Compressive Strength (Ultimate): 74 MPa
- ⊕ Tensile Strength: 40 MPa
- ⊕ Dielectric Constant: 25°C = 3.47
- ⊕ Volume Resistivity, 50°C: 15.8 x 10¹⁰ ohm.cm

Application Notes - General

Preparation

Ensure surfaces are prepared for adhesion or release as desired. Megapoxy 55 will adhere strongly to most clean dry surfaces.

Mixing and Placement

Premix Part A compound to ensure any settled material is recombined. Pour contents of Part B into Part A in correct proportions and mix thoroughly for 3-5 minutes with a power mixer, or flat stirrer by hand, ensure all material around bottom and sides of container is incorporated. Do not aerate mix. Allow mixed material to stand for 2 - 3 minutes for any air to escape then pour into mould in slow stream avoiding air entrapment. Do not apply at temperatures below 10°C.

Working Time (Pot Life)

1 hour at 25°C
30 minutes at 35°C

Cure Time

24 hours at 25°C

Cleaning

Spillage and excess should be cleaned up as soon as possible. Uncured Megapoxy E can be removed using Megapoxy Thinners. Once the product has cured only severe heat or prolonged immersion in a powerful solvent will break it down.

Storage

MEGAPOXY 55 has a shelf life exceeding one year sealed in the original containers and stowed in a dry environment at 15°C to 30°C.

Safety Precautions

Avoid contact with uncured product at all times. Use protective clothing including safety glasses and apply a barrier cream to skin areas that could be exposed. Refer to Material Safety Data Sheets for further information.

First Aid

If swallowed, DO NOT induce vomiting, give a glass of water and contact a Doctor or the Poisons Information Centre. If in eyes, hold eyes open and flood with copious amounts of clean water for at least 15 minutes and contact a Doctor. If skin contact occurs, remove contaminated clothes and wash skin with soap and warm water. If allergic response (irritation, wheezing, etc.) occurs seek medical advice. Refer to Material Safety Data Sheets for further information.

NOTE

As conditions may vary considerably in consuming industries, buyers and users must assess this product's performance for their own requirements.

Manufactured by
Vivacity Engineering Pty. Ltd.
A.C.N. 001 666 557
3 Sefton Road Thornleigh NSW 2120
Phone: (02) 875 3044
QUALITY ASSURANCE TO AS 3902
NATA Accreditation. Reg. N^o 6219



Distributed by:

Permotech

Phone (08) 9303 4655

Fax (08) 9303 4677

U1/4 Achievement Way
Wangara WA 6065