

## Megapoxy 240

Megapoxy 240 is a amber coloured semi rigid epoxy that sets soft after curing, enabling it to be removed after casting if necessary.

Megapoxy 240 is supplied in a 390 gram kit,

It is recommend that the complete kit is used by adding Part A to part B and stirred until uniform using a flat stirrer. Pour into another container and mix again to ensure all the contents are mixed thoroughly before pouring into position. Please note that either component will not cure by itself and requires thorough and complete mixing with correct proportion of resin and hardener.

Mix ratio:

90 Gram Part A : 300 Gram Part B

Mixed Viscosity: approx., 4500 – 5000 cps

Pot Life: 120 – 150 MINUTES

Cure Time: 24 HOURS

Specific Gravity:

PART A – 1.10 – 1.12

PART B - 0.96 – 0.99

VISCOSITY:

PART A 400 – 550 CENTIPOISE

PART B 5000 – 6500 CENTIPOISE

To keep mixing implements and working tools clean use Megapoxy Thinners. Use disposable rubber gloves to protect hands and maintain proper industrial hygiene. For further details to the MSDS.



**VIVACITY ENGINEERING PTY. LTD.**

3 Sefton Road, Thornleigh, NSW 2120 • P.O. Box 71, Hornsby, NSW Australia, 1630  
Telephone +61-2-9875 3044 Fax +61-2-9875 3665 email: info@megapoxy.com  
www.megapoxy.com A.B.N. 78 305 545 664